

# Resistance to Staining and Reagents – BBT™

- 0:** No Stain  
**1:** Slight  
**2:** Moderate  
**3:** Severe  
**Bl:** Bleaching  
**D:** Dulling  
**S:** Softening  
**R:** Reagent left a residue

	BBT MIGRATIONS
<b>Organic Solvents</b>	
Acetone	0, Bl
Chloroform	0, Bl
Ethyl Acetate	0, Bl
Ethyl (Denatured) Alcohol	0
Ethyl Ether	0
Ethylene Glycol (Antifreeze)	0
Formaldehyde – 10%	0
Gasoline	0
Isopropyl Alcohol	0
Kerosene	0, Bl
Methylene Chloride	0, Bl
Methyl ethyl ketone (M.E.K.)	0, Bl
Mineral Spirits	0
Perchloroethylene	0, Bl
Toluene	0, Bl
Trichloroethylene	0, Bl
Turpentine	0
Xylene	0, Bl
<b>Alkali (Bases)</b>	
Ammonium Hydroxide – 30%	0
Potassium Hydroxide – 15%	0
Sodium Hydroxide – 50%	0
<b>Acids</b>	
Acetic Acid – 28%	0, D
Acetic Acid – Glacial	0, D
Hydrochloric – 38%	0, D
Lactic Acid – 10%	1, Bl
Nitric Acid – 15%	0
Phosphoric Acid – 85%	1, Bl
Sulfuric Acid – 40%	1, Bl
Sulfuric Acid – 10%	1, Bl
<b>Salt Solutions</b>	
Calcium Chloride – Sat'd	0
Copper Sulfate – 10%	1
Ferric Chloride – 10%	2
Silver Nitrate – 1%	0
<b>Medical Stains &amp; Reagents</b>	
Aniline Blue – 2.5%	1
Auramine Rhodamine	2
Basic Fuchsin	3
Betadine® Skin Cleanser	1
Betadine Solution – 10%	1
Bromocresol Green	1
Carbol Fuchsin	3
Eosin – 1%	1
Gentian Violet – 2%	3
Glutaraldehyde	0
Iodine Tincture	3
Iodine Gram Stain	2
Iodoform – 1%	0
Lugol's Solution	3
Merthiolate Tincture	2
Methylene Blue	2
Picric Acid – 1%	2
Potassium Permanganate – 0.5%	2
Tincture of Benzoin	2, R
Urea Solution	0
Wright's Blood Stain	2
<b>Embalming Chemicals</b>	
Pretresol – Pre-injection	0, D
Kelcavex – Cavity	0, D
Kelspecial® – Arterial	0, D
Presinol – Arterial	0, D
<b>Disinfectants and Cleaners</b>	
Clorox®	0
Comet® Bathroom Cleaner	0, D
Hydrogen Peroxide	0
Lysol® Liquid Disinfectant	0, D
<b>Food Service</b>	
Catsup	0
Coffee – Hot Black	0
Cola Drink	0
French Dressing	0
Mustard	2
Red Food Color	2
Red Wine	1
Soy Sauce	0
Spaghetti Sauce	0
Tea – Hot Black	1
Tomato Paste	0
<b>Office</b>	
Ball Pen Ink	3
Carbon Paper Smudge	2
Fountain Pen Ink	2
Lead Pencil	2
Permanent Black Marker	3
Photo Copy Toner (Powder)	0
Red Crayon	2
Red Tempura Paint	1
<b>Oils</b>	
Beef Tallow – Hot	0
Canola Oil	0
Cottonseed Oil	0
Brake Fluid	0, D
Dextron Transmission Fluid	0
Mineral Oil	0
Olive Oil	0
SAE #10 Oil	0
30 wt. Non-Detergent Oil	0
Used Motor Oil	0
<b>Miscellaneous</b>	
Asphalt Driveway Sealer	1
Blue Chalk	1
Black Rit Dye	1
Eye Shadow	3
Hair Color	1
Lipstick	1
Perfume	0, Bl
Red Candle Wax	1
Red Nail Polish	3, R
Shoe Polish – Liquid Brown	1
Shoe Polish – Paste Brown	3

Samples were tested as manufactured (no additional surface treatments). All samples were exposed to reagents for four hours (uncovered), then cleaned with a neutral commercial cleaner and cotton cloth. A key for interpreting results is found above. It is important to note that in some cases residual stain, residues and surface dulling may be further reduced or eliminated with different or more aggressive cleaning procedures and/or cleaning agents than the common method used for this multi-product comparison. For further details on appropriate cleaning methods and care for specific products, please consult the care and maintenance guidelines for the specific product at [armstrong.com/flooring](http://armstrong.com/flooring).

Betadine® is a registered trademark of Purdue Products, L.P.  
 Kelspecial® is a registered trademark of Kelco Supply Company  
 Clorox® is a registered trademark of The Clorox Company  
 Comet® is a registered trademark of The Comet Products Corporation  
 Lysol® is a registered trademark of Linden Corporation